WeConnectScience

LG Chem

LS070

Description

LS070, homopolymer made by suspension polymerization can be applied to injection and calendering process.

Application

Fitting, Tile, Deco Sheet, Board Sheet, Foam Board Sheet,
Automotive Parts, Package

Properties	Method	Unit	LS070	Condition
Degree of Polymerization	LG Method PVC03		700±30	
K-value			58	
Particle Size	LG Method PVC04	%	Max 0.07	45 Mesh
Bulk Density	LG Method PVC01	g/cm³	0.61±0.03	
Density			1.4	23℃
Volatiles	LG Method PVC02	%	Max 0.20	

Issued Date : 2022-02-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.